


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B32B 27/12		A1	(11) International Publication Number: WO 95/04654
			(43) International Publication Date: 16 February 1995 (16.02.95)
(21) International Application Number: PCT/US94/08736 (22) International Filing Date: 3 August 1994 (03.08.94) (30) Priority Data: 08/104,791 11 August 1993 (11.08.93) US (71) Applicant: CLOPAY PLASTIC PRODUCTS COMPANY, INC. [US/US]; Suite 1600, 312 Walnut Street, Cincinnati, OH 45202 (US). (72) Inventor: WU, Pai-Chuan; 11053 Huntwicke Place, Cincinnati, OH 45241 (US). (74) Agents: JOSEPHIC, David, J. et al.; Wood, Herron & Evans, 2700 Carew Tower, Cincinnati, OH 45202 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	

(54) Title: AN ELASTIC LAMINATED SHEET OF AN INCREMENTALLY STRETCHED NONWOVEN FIBROUS WEB AND ELASTOMERIC FILM AND METHOD



(57) Abstract

An elastic laminated sheet of an incrementally stretched nonwoven fibrous web (9) and elastomeric film (13) having a multitude of fibers extending outwardly from the laminated surface and method of making are disclosed. The elastic laminates are especially useful in diapers, surgical gowns, sheets, dressings, hygienic products and the like.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Larvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

-1-

AN ELASTIC LAMINATED SHEET OF AN INCREMENTALLY STRETCHED
NONWOVEN FIBROUS WEB AND ELASTOMERIC FILM AND METHOD

BACKGROUND OF THE INVENTION

Processes of bonding nonwoven fibrous webs to thermoplastic films have been known for some time. Additionally, methods for extrusion laminating thermoplastic films to unstretched nonwoven webs are well known in the art.

Relevant patents regarding extrusion lamination of unstretched nonwoven webs include U.S. Patent Nos. 2,714,571; 3,058,863; 4,522,203; 4,614,679; 4,692,368; 4,753,840 and 5,035,941. The above '863 and '368 patents disclose stretching extruded polymeric films prior to laminating with unstretched nonwoven fibrous webs at pressure roller nips. The '203 and '941 patents are directed to co-extruding multiple polymeric films with unstretched nonwoven webs at pressure roller nips. The '840 patent discloses preforming nonwoven polymeric fiber materials prior to extrusion laminating with films to improve bonding between the nonwoven fibers and films. More specifically, the '840 patent discloses conventional embossing techniques to form densified and undensified areas in nonwoven base plies prior to extrusion lamination

-2-

to improve bonding between nonwoven fibrous webs and films by means of the densified fiber areas. The '941 patent also teaches that unstretched nonwoven webs that are extrusion laminated to single ply polymeric films are susceptible to pinholes caused by fibers extending generally vertically from the plane of the fiber substrate and, accordingly, this patent discloses using multiple co-extruded film plies to prevent pinhole problems. Furthermore, methods for bonding loose nonwoven fibers to polymeric film are disclosed in U.S. Patent Nos. 3,622,422; 4,379,192 and 4,725,473.

It has also been known to stretch nonwoven fibrous webs using intermeshing rollers to reduce basis weight and examples of patents in this area are U.S. Patent Nos. 4,153,664 and 4,517,714. The '664 patent discloses a method of incremental cross direction (CD) or machine direction (MD) stretching nonwoven fibrous webs using a pair of interdigitating rollers to strengthen and soften nonwoven webs. The '664 patent also discloses an alternative embodiment wherein the nonwoven fibrous web is laminated to the thermoplastic film prior to intermesh stretching.

There is a continuing need for improved laminates of nonwoven fibrous substrates in plastic films that provide sufficient absorbency and softness. It would be very desirable to further improve the properties of such laminates and to expand their utilities in articles of clothing and other useful products. Improvements are also

-3-

desirable in methods of producing such laminates on high speed production machinery.

SUMMARY OF THE INVENTION

This invention is directed to an elastic
5 laminated sheet of a nonwoven fibrous web and an
elastomeric film. The term "elastic" is used in the
specification and claims as meaning stretchable under force
and recoverable to its original or essentially original
form upon release of that force. The fibrous web has a
10 multitude of fibers extending outwardly from the laminated
surface that are formed by incremental stretching of the
laminated sheet along lines substantially uniformly across
the laminated sheet and throughout its depth. The
laminated elastomeric film is stretchable and recoverable
15 to provide elasticity to the laminated sheet.

This invention also provides a method for
producing the elastic laminate on high speed production
machinery at line speeds of about 500 fpm. Thus, this
invention provides for laminates of nonwoven fibrous
20 substrates and elastomeric films that have sufficient
absorbency and softness with new properties of
stretchability and recoverability. The unique laminates
and properties enable the laminated sheet to be used for
many purposes including particularly articles of clothing
25 where stretchability and recoverability are significant
properties.

The elastic laminated sheet comprises a nonwoven
fibrous web and an elastomeric film laminated to at least

-4-

one web surface. The elastomeric film may be on one side of the nonwoven or between the nonwovens to form the elastic laminate. The laminate is incrementally stretched along lines substantially uniformly across its length and width and throughout its depth to form a stretchable and recoverable composite. Thus, stretched zones may be separated or bordered by unstretched zones in the laminate to provide elasticity to the laminate. Elasticity in the composite is mainly attributable to the elastic film.

Under elongation or deformation forces, the laminate is stretchable and thus would conform, for example, to parts of the body when employed as a fabric in an article of clothing. Similarly, with the unique property of elastic recovery, the laminate will essentially return to its original state. Furthermore, it may be repeatedly subjected to stretching and recovery.

In a most preferred form, the method of this invention involves lamination by extrusion or adhesion of the nonwoven fibrous web to the elastomeric film.

Preferably the method may be conducted on high speed production machinery on the order of about 500 fpm. It involves inline lamination and incremental stretching. More specifically, a nonwoven fibrous web is introduced into a nip of rollers for extrusion lamination with an elastomeric film. An elastomeric extrudate is extruded into the nip at a temperature above its softening point to form a film laminated to the fibrous web. The compressive force between the fibrous web and extrudate at the nip is

-5-

controlled to bond one surface of the web to the film to form the laminate. As indicated above, the laminate or composite may also be formed by adhesively bonding the fibrous web to the elastomeric film. The thus formed laminate is then incrementally stretched along lines substantially uniformly across the laminate and throughout its depth to provide an elastic laminated sheet. By applying an incremental stretching force to the laminated sheet, both the web and the film are stretched. Upon removing the stretching force from the laminated sheet, the elastic film recovers its shape and fibers of the web are thereby caused to extend outwardly from the bonded web surface to give loft to the laminated sheet.

Other benefits, advantages and objectives of this invention will be further understood with reference to the following detailed description.

DETAILED DESCRIPTION

It is a primary objective of this invention to produce an elastic laminated sheet of a nonwoven fibrous web and an elastomeric film on high speed production machinery to produce recoverable and stretchable laminates. It is a further objective to produce such laminates having satisfactory bond strengths while maintaining the appearance of fabric and soft feel. As developed above, these and other objectives are achieved in preferred form of the invention by first incrementally stretching a laminated sheet of nonwoven fibrous web and elastomeric film along lines substantially uniformly across the

-6-

laminate and throughout its depth. It has been found, by incrementally stretching the laminate, that an elastic sheet material is produced where the fibrous web is bonded to the elastomeric film, yet the sheet is stretchable and recoverable to essentially its original state. Furthermore, it has been found that such a laminated composite may be made by extrusion and stretching inline in order to achieve production speeds on the order of about 500 fpm. The elastic laminate in one form is characterized by being impervious to the passage of fluid by virtue of the elastomeric film while maintaining a soft feel on the fibrous web surface of the laminate. Alternatively, various degrees of vapor or air permeability may be achieved in the laminate or composite by providing mechanical microvoids, for instance. In a preferred form, the elastic laminate of this invention has the desirable feature of soft feel to achieve utility in a number of applications including diapers, pants, surgical gowns, sheets, dressings, hygienic products and the like.

A. Materials for the Laminate

The elastomeric film preferably is of the polyolefin type that is processable into a film for direct lamination by melt extrusion onto the fibrous web in one embodiment. Suitable elastomeric polymers may also be biodegradable or environmentally degradable. Suitable elastomeric polymers for the film include poly(ethylene-butene), poly(ethylene-hexene), poly(ethylene-octene), poly(ethylene-propylene), poly(styrene-butadiene-styrene),

-7-

poly(styrene-isoprene-styrene), poly(styrene-ethylene-butylene-styrene), poly(ester-ether), poly(ether-amide), poly(ethylene-vinylacetate), poly(ethylene-methylacrylate), poly(ethylene-acrylic acid),
5 poly(ethylene butylacrylate), polyurethane, poly(ethylene-propylene-diene), ethylene-propylene rubber. A new class of rubber-like polymers may also be employed and they are generally referred to herein as polyolefins produced from single-site catalysts. The most preferred catalysts are
10 known in the art as metallocene catalysts whereby ethylene, propylene, styrene and other olefins may be polymerized with butene, hexene, octene, etc., to provide elastomers suitable for use in accordance with the principles of this invention, such as poly(ethylene-butene), poly(ethylene-hexene),
15 poly(ethylene-octene), poly(ethylene-propylene) and/or polyolefin terpolymers thereof.

The nonwoven fibrous web may comprise fibers of polyethylene, polypropylene, polyesters, rayon, cellulose, nylon, and blends of such fibers. A number of definitions
20 have been proposed for nonwoven fibrous webs. The fibers are usually staple fibers or continuous filaments. As used herein "nonwoven fibrous web" is used in its generic sense to define a generally planar structure that is relatively flat, flexible and porous, and is composed of staple fibers
25 or continuous filaments. For a detailed description of nonwovens, see "Nonwoven Fabric Primer and Reference Sampler" by E. A. Vaughn, Association of the Nonwoven Fabrics Industry, 3d Edition (1992). The nonwovens may be

-8-

carded, spun bonded, wet laid, air laid and melt blown as such products are well known in the trade.

In a preferred form, the elastic laminated sheet employs an elastomeric film having a gauge or a thickness between about 0.25 and 10 mls and, depending upon use, the film thickness will vary and, most preferably, in disposable applications is the order of about 0.25 to 2 mils in thickness. The nonwoven fibrous webs of the laminated sheet normally have a weight of about 10 grams per square yard to 60 grams per square yard preferably about 20 to about 40 grams per square yard. When employing adhesive lamination, adhesives such as hot melt adhesive, water base adhesive or solid base adhesive may be used. The composite or laminate can be incrementally stretched in the cross direction (CD) to form a CD stretchable and recoverable composite. Furthermore, CD stretching may be followed by stretching in the machine direction (MD) to form a composite which is stretchable and recoverable in both CD and MD directions. As indicated above, the composite or laminate may be used in many different applications such as baby diapers, baby training pants, catamenial pads and garments, and the like where stretchable and recoverable properties, as well as fluid barrier properties are needed.

B. Stretchers For the Laminates

A number of different stretchers and techniques may be employed to stretch the starting or original laminate of a nonwoven fibrous web and elastomeric film.

-9-

Laminates of nonwoven carded fibrous webs of staple fibers or nonwoven spun-bonded fibrous webs may be stretched with the stretchers and techniques described as follows:

1. Diagonal Intermeshing Stretcher

5 The diagonal intermeshing stretcher consists of a pair of left hand and right hand helical gear-like elements on parallel shafts. The shafts are disposed between two machine side plates, the lower shaft being located in fixed bearings and the upper shaft being located
10 in bearings in vertically slidable members. The slidable members are adjustable in the vertical direction by wedge shaped elements operable by adjusting screws. Screwing the wedges out or in will move the vertically slidable member respectively down or up to further engage or disengage the
15 gear-like teeth of the upper intermeshing roll with the lower intermeshing roll. Micrometers mounted to the side frames are operable to indicate the depth of engagement of the teeth of the intermeshing roll.

 Air cylinders are employed to hold the slidable
20 members in their lower engaged position firmly against the adjusting wedges to oppose the upward force exerted by the material being stretched. These cylinders may also be retracted to disengage the upper and lower intermeshing rolls from each other for purposes of threading material
25 through the intermeshing equipment or in conjunction with a safety circuit which would open all the machine nip points when activated.

-10-

A drive means is typically utilized to drive the stationery intermeshing roll. If the upper intermeshing roll is to be disengageable for purposes of machine threading or safety, it is preferable to use an
5 antibacklash gearing arrangement between the upper and lower intermeshing rolls to assure that upon reengagement the teeth of one intermeshing roll always fall between the teeth of the other intermeshing roll and potentially damaging physical contact between addendums of intermeshing
10 teeth is avoided. If the intermeshing rolls are to remain in constant engagement, the upper intermeshing roll typically need not be driven. Drive may be accomplished by the driven intermeshing roll through the material being stretched.

15 The intermeshing rolls closely resemble fine pitch helical gears. In the preferred embodiment, the rolls have 5.935" diameter, 45° helix angle, a 0.100" normal pitch, 30 diametral pitch, 14 1/2° pressure angle, and are basically a long addendum topped gear. This
20 produces a narrow, deep tooth profile which allows up to about 0.090" of intermeshing engagement and about 0.005" clearance on the sides of the tooth for material thickness. The teeth are not designed to transmit rotational torque and do not contact metal-to-metal in
25 normal intermeshing stretching operation.

2. Cross Direction Intermeshing Stretcher

The CD intermeshing stretching equipment is identical to the diagonal intermeshing stretcher with

-11-

differences in the design of the intermeshing rolls and other minor areas noted below. Since the CD intermeshing elements are capable of large engagement depths, it is important that the equipment incorporate a means of causing the shafts of the two intermeshing rolls to remain parallel when the top shaft is raising or lowering. This is necessary to assure that the teeth of one intermeshing roll always fall between the teeth of the other intermeshing roll and potentially damaging physical contact between intermeshing teeth is avoided. This parallel motion is assured by a rack and gear arrangement wherein a stationary gear rack is attached to each side frame in juxtaposition to the vertically slidable members. A shaft traverses the side frames and operates in a bearing in each of the vertically slidable members. A gear resides on each end of this shaft and operates in engagement with the racks to produce the desired parallel motion.

The drive for the CD intermeshing stretcher must operate both upper and lower intermeshing rolls except in the case of intermeshing stretching of materials with a relatively high coefficient of friction. The drive need not be antibacklash, however, because a small amount of machine direction misalignment or drive slippage will cause no problem. The reason for this will become evident with a description of the CD intermeshing elements.

The CD intermeshing elements are machined from solid material but can best be described as an alternating stack of two different diameter disks. In the preferred

-12-

embodiment, the intermeshing disks would be 6" in diameter, 0.031" thick, and have a full radius on their edge. The spacer disks separating the intermeshing disks would be 5 1/2" in diameter and 0.069" in thickness. Two rolls of this configuration would be able to be intermeshed up to 0.231" leaving 0.019" clearance for material on all sides. As with the diagonal intermeshing stretcher, this CD intermeshing element configuration would have a 0.100" pitch.

10 3. Machine Direction Intermeshing Stretcher

The MD intermeshing stretching equipment is identical to the diagonal intermeshing stretch except for the design of the intermeshing rolls. The MD intermeshing rolls closely resemble fine pitch spur gears. In the preferred embodiment, the rolls have a 5.933" diameter, 0.100" pitch, 30 Diametral pitch, 14 1/2° pressure angle, and are basically a long addendum, topped gear. A second pass was taken on these rolls with the gear hob offset 0.010" to provide a narrowed tooth with more clearance. With about 0.090" of engagement, this configuration will have about 0.010" clearance on the sides for material thickness.

 4. Incremental Stretching Technique

The above described diagonal, CD or MD intermeshing stretchers may be employed to produce the incrementally stretched laminate of nonwoven fibrous web and elastomeric film of this invention. The stretching operation is usually employed on an extrusion laminate of

-13-

a nonwoven fibrous web of staple fibers or spun-bonded filaments and elastomeric film. In one of the unique aspects of this invention an elastic laminate of a nonwoven fibrous web of spun-bonded filaments may be incrementally stretched to provide a very soft fibrous finish to the laminate that looks like carded fibers with superior bond strengths. The laminate of woven fibrous web and elastomeric film is incrementally stretched using, for instance, the CD intermeshing stretcher with one pass through the stretcher with a depth of roller engagement at about 0.090 inch to 0.120 inch at speeds from about 500 fpm to 1000 fpm or faster. The results of such CD incremental or intermesh stretching produces laminates or composites that have excellent stretchability and recoverability and yet provide superior bond strengths and soft fibrous textures.

DETAILED EXAMPLES OF THE INVENTION

The following examples illustrate the elastic laminates of this invention and methods of making them. In light of these examples and this further detailed description, it is apparent to a person of ordinary skill in the art that variations thereof may be made without departing from the scope of this invention.

The invention is further understood with reference to the drawings in which:

Fig. 1 is a schematic of an inline extrusion lamination and incremental stretching apparatus for making the laminate of this invention.

-14-

Fig. 2 is a cross sectional view taken along the line 2-2 of Fig. 1 illustrating the intermeshing rollers in diagrammatic form.

Fig. 3 is a magnified diagrammatic sketch in cross-section of a nonwoven fibrous web laminated to the elastomeric film before stretching.

Fig. 4 is a magnified diagrammatic sketch of the laminate of Fig. 3 after incremental stretching to provide a composite where the fibers of the web are caused to extend outwardly from the surface to give high loft to the laminated sheet that is stretchable and recoverable according to the principles of this invention.

Fig. 5 is a graph demonstrating the elongation properties of comparative examples.

Fig. 6 is a graph demonstrating the elongation properties of elastic laminated sheets of this invention for comparison with comparative extrusion laminated composites.

COMPARATIVE EXAMPLES I-1 and II-2

Extrusion lamination of low density polyethylene (LDPE) film to a nonwoven fibrous web was made for direct comparison with an elastic extrusion laminate that was incrementally stretched according to this invention.

I-1. Extrusion Laminate of Nonwoven Fibrous Web and Thermoplastic Film (Without Incremental Stretching)

Two carded polypropylene nonwoven fibrous webs of 26 grams/yd² weight were laminated by extrusion of a LDPE thermoplastic film with a density of 0.914 g/cc at one

-15-

mil between the webs according to the comparative extrusion lamination technique as shown in the extrusion lamination section of Fig. 1. As shown schematically in Fig. 1, the incoming webs 9,9 from rollers 13, 13 were introduced into the nip of a rubber roll 5 and a metal roll 4. The LDPE film 3 from extruder 1 was extruded through die 2 into the nip while the two carded fibrous webs 9,9 were introduced. Typically, at speeds over 500 fpm in this extrusion lamination section, the polyethylene film 3 on the order of about 0.25 to 10 mils in thickness is laminated at melt temperatures on the order of about 500-625°F to form the laminate 12 which is taken off at roller 7. The compressive force at the nip is controlled such that the webs are bonded to the polyolefin film to avoid pinholing and preserve the fibrous feel on the fiber surfaces of the laminate 12. Pressures on the order of about 10 to 80 psi are sufficient to achieve satisfactory bond for fibrous webs of about 10 to 60 grams/yd². In this example, the laminate is tested for its stretchability using an Instron Tensile Tester. A one inch strip cut along its cross machine direction (CD) is stretched at 20"/min. This composite breaks at 45% elongation with an ultimate tensile strength (broken strength) of 3.4 pounds per inch. This composite is not a stretchable and recoverable composite upon stretching and releasing of the stretch force. This is demonstrated in Fig. 5, (Comparative Example I-1).

-16-

I-2. Extrusion Laminate of Nonwoven Fibrous
Web and Thermoplastic Film With
Incremental Stretching

When the composite of Comparative Example I-1 is
5 incrementally stretched with reference to the incremental
stretched section of Fig. 1, the composite can then be
stretched to more than 50% elongation. The stretching
operation is schematically shown where the incoming web 12
was passed through the CD stretcher rollers 10 and 11 at
10 a depth of roller engagement at about 0.100 inch at about
500 fpm. The intermeshing rollers 10 and 11 are
diagrammatically shown in Fig. 2 to illustrate the uniform
stretching along lines across the laminate and through the
depth of the laminate. The elastic property of the
15 modified composite is then tested according to its stress
(tensile force) and strain (elongation) by using an Instron
Tensile Tester (see Fig. 5, Example I-2). The permanent
set of this modified composite when stretched to 50% is 20%
(see Fig. 5, Example I-2). "Permanent set" means the final
20 unrecoverable dimension of the composite after being
stretched. This non-elastic laminate is not a satisfactory
stretchable and recoverable composite.

-17-

**EXAMPLE II Elastic Laminate of Incrementally Stretched
Nonwoven Fibrous Web and Elastomeric Film**

In this Example the same procedures are followed
5 as for Example I, except the plastic used in extrusion
lamination was DOW Chemical's elastomeric incite resin XU
51800.51 with a density of 0.870 grams per cubic
centimeter. This new elastomeric resin is manufactured by
using ethylene and octene comonomer with a new metallocene
10 catalyst.

The elastic laminate made in this Example, when
CD incrementally stretched using an engagement of 0.100"
is soft, stretchable and recoverable when compared to the
laminate made according to Example I-1, except having a
15 density of 0.870 g/cc. Table 1 and Figure 6 show the
detailed differences. The permanent set of the Example I-1
when stretched to 50% (Figure 6, dotted curve 1), 75%
(Figure 6, dotted curve 2)), and 100% (Figure 6, dotted
curve 3) are 10%, 26% and 38%, respectively. However the
20 laminate becomes much softer and elastic according to this
invention under less force when stretched to 50% (Figure
6, solid curve 4), 75% (Figure 6, solid curve 5) and 100%
(Figure 6, solid curve 6) are 6%, 18% and 24%,
respectively. In its most preferred form, the permanent
25 set of the laminate is no more than about 10% of its
original dimension after first stretching to about 50% of
its original shape.

The force required to stretch the laminate of
Example II according to this invention is less than the

-18-

comparative laminate (see Table 1). The recovery after releasing the force upon stretching is higher (or the permanent set is lower) with the laminate of this invention when compared to the comparative laminate. The product according to this invention will be suitable for diaper application such as the training pant or elastic waist and leg where the recoverable elastic sheet is needed.

The high loft of the stretched elastic laminate is diagrammatically shown (Fig. 4) with reference to one side of the laminate before stretching (Fig. 3). The elastomeric film 3 is bonded to the surface fibers 20 of the web 9 in the extrusion lamination section of Fig. 1. to produce a laminate 12 where only one side is diagrammatically shown in Fig. 3. After incremental stretching, the fibers of the web 9 are caused to extend outwardly and provide a high loft of fibers to the laminate 13 as diagrammatically shown on one side in Fig. 4. The elastomeric film recovers its original or substantially original shape after stretching, whereas the web after stretching will increase in thickness and softness. This is one of the unique features of the laminate and method of this invention.

-19-

Table 1

	COMPARATIVE LAMINATE			LAMINATE OF THIS INVENTION		
TOTAL COMPOSITE WEIGHT (G/YD ²)	68			56		
BOND STRENGTH (G/IN)	TOTAL BOND			TOTAL BOND		
STRETCHED TO AN ELONGATION SPECIFIED (%)	50	75	100	50	75	100
FORCE REQUIRED TO STRETCH TO THE SPECIFIED ELONGATION (LBS/IN)	1.75	2.05	2.10	0.9	1.45	1.90
PERMANENT SET AFTER THE STRETCHING TO THE SPECIFIED ELONGATION (%)	10	26	38	6	18	24
TENSILE STRENGTH AT 10% ELONGATION (LBS/IN)	0.90	0.85	0.75	0.15	0.15	0.15

-20-

Example III

Two 34 grams per square yard of carded polypropylene nonwoven are extrusion laminated to an elastomeric film by using an elastomeric blend of styrene-butadiene-styrene block copolymer and EVA copolymer. The middle layer of the elastomeric film is at 2.0 mils. The composite so produced is then CD incrementally stretched by using an engagement of 0.100". The incrementally stretched laminate according to this invention becomes more stretchable and recoverable upon stretching and releasing of the force when compared to the comparative laminate of the above same elastomer composition without stretching. The force required to stretch the composite according to the invention is also lower. The results are shown in Table 2.

-21-

Table 2

	COMPARATIVE LAMINATE			LAMINATE OF THIS INVENTION		
Stretch to an elongation specified at (%)	50	75	100	50	75	100
Force required to stretch to the specified elongation (lbs/in)	1.25	2.0	2.4	0.25	0.35	0.45
Permanent set after stretching force is released (%)	15	20	26	6	10	12

-22-

Example IV

A 41 grams per square yard carded polypropylene nonwoven is extrusion laminated by using an EPDM elastomer. This laminate is then CD incrementally stretched with a CD stretcher engagement of 0.100". The laminate becomes soft, stretchable and recoverable upon stretching and releasing of the stretch force and may be compared to the comparative laminate of same composition without incremental stretching as shown in the test results of Table 3.

-23-

Table 3

	COMPARATIVE LAMINATE			LAMINATE OF THIS INVENTION		
Stretch to an elongation specified at (%)	50	75	100	50	75	100
Force required to stretch to the specified elongation (lbs/in)	1.2	1.5	1.6	0.5	0.7	0.9
Permanent set after stretching force is released (%)	10	18	24	9	15	17

-24-

Example V

A Scot carded polypropylene nonwoven with 30 grams per square yard and 2.0 mils of EPDM film is adhesively laminated by using an H. P. Fuller's EVA hot melt adhesive 2835. This laminated sheet is then incrementally stretched by using the CD stretcher at 0.100" engagement to produce a soft and elastic sheet. A comparative laminate of the same composition without incremental stretching was also run. Table 4 shows the test results.

-25-

Table 4

	COMPARATIVE LAMINATE			LAMINATE OF THIS INVENTION		
	<hr/>			<hr/>		
Stretch to an elongation specified at (%)	50	75	100	50	75	100
Force required to stretch to the specified elongation (lbs/in)	2.2	2.6	2.8	0.9	1.5	2.0
Permanent set after stretching force is released (%)	8	19	25	6	14	18

-26-

Exempl VI

A DuPont sontara polyester fabric grade 8000 is extrusion laminated to DuPont polyester elastomer (Hytrel 8206) at 1.0 mil. The laminated sheet is then CD incrementally stretched by a CD incremental stretcher with an engagement of 0.100" to produce a soft, elastic, stretchable and recoverable composite. A comparative laminate of the same composition without incremental stretching was also run. Table 5 shows the test results.

-27-

Table 5

	COMPARATIVE LAMINATE			LAMINATE OF THIS INVENTION		
	<hr/>			<hr/>		
Stretch to an elongation specified at (%)	50	75	100	50	75	100
Force required to stretch to the specified elongation (lbs/in)	1.6	2.2	3.0	0.7	0.8	1.1
Permanent set after stretching force is released (%)	18	32	42	8	17	23

-28-

Example VII

A DuPont sontara polyester fabric grade 8000 is adhesive laminated to DuPont hytrel 8206 at 1.0 mil by using H. B. Fuller EVA hot melt adhesive 2835. The adhesive
5 laminated sheet is then CD incrementally stretched by using a CD engagement of 0.08" followed with a MD stretching by using an engagement also of 0.08". The laminate is both a CD and MD stretchable and recoverable elastic composite. A comparative laminate of the same composition without
10 incremental stretching was also run. The test results are shown on Table 6.

-29-

Table 6

COMPARATIVE LAMINATE

LAMINATE OF THIS INVENTION

Stretch to an elongation specified at (%)	COMPARATIVE LAMINATE				LAMINATE OF THIS INVENTION							
	50%	75%	100%		50%	75%	100%					
Direction	MD	CD	MD	CD	MD	CD	MD	CD				
Force required to stretch to the specified elongation (lbs/in)	NA*	2.2	NA*	3.5	NA*	5.0	0.8	0.7	1.1	1.0	1.3	1.1
Permanent set after stretching	NA*	16	NA*	25	NA*	30	10	7	20	17	22	20

*NA - the material broke at 45% elongation

-30-

Example VIII

Exxon's Exact polymer type 4011 of ethylene and octene manufactured by using a Metallocene catalyst at a density of 0.885g/cc extrusion laminated to DuPont's polyester sontara fabric grade 8000.

This extrusion laminated sheet is then CD incrementally stretched with an engagement of 0.090" followed with MD incremental stretching with an engagement of 0.065". The laminate is both CD and MD stretchable and recoverable. A comparative laminate of the same composition without incremental stretching was also run. Table 7 shows the test results.

Table 7

COMPARATIVE LAMINATE				LAMINATE OF THIS INVENTION							
Stretch to an elongation specified at (%)	50%	75%	100%	50%		75%		100			
				MD	CD	MD	CD	MD	CD	MD	CD
Direction	MD	CD	MD	CD	MD	CD	MD	CD	MD	CD	CD
Force required to stretch to the specified elongation (lbs/in)	NA* 1.35	NA*	1.75	NA* 2.40	0.75	0.75	1.05	0.9	1.25	1.05	
Permanent set after stretching	NA* 15	NA*	34	NA* 47	10	10	20	20	26	30	

*NA - the material broke at 45% elongation

-32-

The above data and experimental results demonstrate the unique stretchable and recoverable properties of the elastic laminated sheets of this invention. Other variations will be apparent to a person of skill in the art without departing from this invention.

-33-

What is claimed is:

1. An elastic laminated sheet of a nonwoven fibrous web and an elastomeric film comprising an elastomeric film and a nonwoven fibrous web laminated to a surface of said film to provide said laminated sheet, said laminated sheet having a multitude of fibers extending outwardly from said laminated surface formed by incremental stretching of the laminated sheet along lines substantially uniformly across the laminated sheet and throughout its depth, said laminated sheet being stretchable and recoverable.
2. The elastic laminated sheet of claim 1 formed by extrusion or adhesive lamination.
3. The elastic laminated sheet of claim 1 wherein said fibrous web comprises fibers selected from the group consisting of polypropylene, polyethylene, polyester, cellulose, rayon, nylon and blends of two or more of such fibers.

-34-

4. The elastic laminated sheet of claim 1 wherein the polymer of said elastomeric film is selected from the group consisting of poly(ethylene-butene), poly(ethylene-hexene), poly(ethylene-octene), poly(ethylene-propylene),
5 poly(styrene-butadiene-styrene), poly(styrene-isoprene-styrene), poly(styrene-ethylene-butylene-styrene), poly(ester-ether), poly(ether-amide), poly(ethylene-vinylacetate), poly(ethylene-methylacrylate), poly(ethylene-acrylic acid), poly(ethylene butylacrylate), polyurethane,
10 poly(ethylene-propylene-diene), and ethylene-propylene rubber.

5. The elastic laminated sheet of claim 1 wherein said film has a thickness on the order of about 0.25 to about 10 mils.

6. The elastic laminated sheet of claim 1 wherein said nonwoven fibrous web has a weight of about 10 grams/square yard to about 60 grams/square yard.

7. The elastic laminated sheet of claim 1 wherein said elastomeric film has a thickness on the order of about 0.25 to about 2 mils and the nonwoven fibrous web has a weight on the order of about 20 to about 40 grams/square yard.

-35-

8. The elastic laminated sheet of claim 1 incrementally stretched in a cross direction to form a stretchable and recoverable composite in said cross direction.

9. The elastic laminated sheet of claim 1 incrementally stretched in both its cross direction and longitudinal direction to form a stretchable and recoverable composite which is stretchable and recoverable in both said
5 cross and longitudinal directions.

10. The elastic laminated sheet of claim 1 having a permanent set after being stretched to 50% of its original shape of no more than about 10%.

11. The elastic laminated sheet of claim 1 wherein said elastomeric film has opposite surfaces and a nonwoven fibrous web is laminated to both surfaces to provide said laminated sheet.

-36-

12. The elastic laminated sheet of claim 1 wherein the polymer of said elastomeric film is a polyolefin polymer produced by a single cite catalyst.

13. The elastic laminated sheet of claim 12 wherein the polyolefin is derived from the polymerization of monomers selected from the group consisting of ethylene, propylene, styrene, butene, hexene and octene, and mixtures thereof.

14. A method of making an elastic laminated sheet of a nonwoven fibrous web and an elastomeric film comprising introducing a nonwoven fibrous web and an elastomeric film into a bonding station,

10 controlling the compressive force between said web and film at the bonding station to bond a surface of the web to said film to form a laminated sheet, said laminated film being elastic and having an original shape,

15 applying an incremental stretching force to said laminated sheet along lines substantially uniformly across the laminated sheet and throughout its depth to stretch the web and said film,

20 removing said stretching force from the laminated sheet whereby said elastic film substantially recovers its shape and fibers of said web are thereby caused to extend outwardly from said bonded web surface to give loft to said laminated sheet.

-37-

15. The method of claim 14 wherein the bonding station is a nip of rollers and film is bonded to said web at the nip by extruding an elastomeric extrudate at a temperature above its softening point into the nip to form
5 a film for bonding with said web.

16. The method of claim 14 wherein said film is bonded to said web by means of adhesive.

17. The method of claim 14 comprising the further steps of extruding said film into a nip of rollers for extrusion lamination with said nonwoven fibrous web by introducing said web into said nip and subsequently
5 incrementally stretching inline said laminate.

-38-

18. A method of making an elastic laminated sheet of a nonwoven fibrous web and an elastomeric film comprising introducing a nonwoven fibrous web and an elastomeric film into a nip of rollers,

5 controlling the compressive force between said fibrous web and film at the nip to bond the surface of the web to said film to form a laminated sheet, said film being elastic and having an original shape,

10 applying an incremental stretching force to said laminated sheet along lines substantially uniformly across the laminated sheet and throughout its depth to stretch the web and the film,

15 removing said stretching force from the laminated sheet whereby said elastic film substantially recovers its shape and fibers of said web are thereby caused to extend outwardly from said bonded web surface to give loft to said laminated sheet.

19. The method of claim 18 wherein said laminated sheet is formed by extrusion or adhesive lamination.

20 20. The method of claim 18 wherein said fibrous web comprises fibers selected from the group consisting of polypropylene, polyethylene, polyester, cellulose, rayon, nylon and blends of two or more of such fibers.

-39-

21. The method of claim 18 wherein the polymer of said elastomeric film is selected from the group consisting of poly(ethylene-butene), poly(ethylene-hexene), poly(ethylene-octene), poly(ethylene-propylene),
5 poly(styrene-butadiene), poly(styrene-isoprene-styrene), poly(styrene-ethylene-butylene-styrene), poly(ester-ether), poly(ether-amide), poly(ethylene-vinylacetate), poly(ethylene-methylacrylate), poly(ethylene-acrylic acid), poly(ethylene butylacrylate), polyurethane, poly(ethylene-
10 propylene-diene), and ethylene-propylene rubber and a polyolefin polymer produced by a single cite catalyst.

22. The method of claim 18 wherein said film has a thickness on the order of about 0.25 to about 10 mils.





23. The method of claim 18 wherein said nonwoven fibrous web has a weight of about 10 grams/square yard to about 60 grams/square yard.

24. The method of claim 18 wherein said elastomeric film has a thickness on the order of about 0.25 to about 2 mils and the nonwoven fibrous web has a weight on the order of about 20 to about 40 grams/square yard.


25. The method of claim 18 incrementally stretched in a cross direction to form a stretchable and recoverable composite in said cross direction.

-40-

26. The method of claim 18 incrementally stretched in both its cross direction and longitudinal direction to form a stretchable and recoverable composite which is stretchable and recoverable in both said cross and
5 longitudinal directions.



2 / 3

**FIG. 5**




FIG. 6

INTERNATIONAL SEARCH REPORT

 Information Application No
 PCT/US 94/08736

 A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 B32B27/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,92 15444 (THE PROCTER & GAMBLE COMPANY) 17 September 1992 see page 1, line 1 - page 3, line 31; figures 4B,4C see page 13, line 30 - page 14, line 27 see page 16, line 23 - line 35 see page 17, line 30 - page 18, line 4 ----	1-3,6,8, 9,14-20, 23,25,26
A	US,A,4 981 747 (MORMAN) 1 January 1991 see column 3, line 34 - line 40 see column 4, line 1 - line 57 see column 5, line 29 - column 6, line 52 see column 10, line 26 - line 31 ----- -/--	1-4,6, 11,14

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

9 December 1994

Date of mailing of the international search report

17. 01. 95

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax (+31-70) 340-3016

Authorized officer

Pamies Olle, S

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/08736

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 187 725 (KIMBERLY-CLARK CORPORATION) 16 July 1986 see page 10, line 21 - line 32; claims see page 12, line 6 - line 9 ---	1-7
A	US,A,4 673 615 (MURPHY ET AL.) 16 June 1987 see column 1, line 22 - column 2, line 2; figures 1,2 -----	1-3

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/US 94/08736

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9215444	17-09-92	US-A- 5167897	01-12-92
		AU-A- 1535192	06-10-92
		BR-A- 9205685	24-05-94
		CN-A- 1064238	09-09-92
		CZ-A- 9301641	16-03-94
		EP-A- 0573586	15-12-93
		JP-T- 6505681	30-06-94
		PT-A- 100180	29-04-94

US-A-4981747	01-01-91	NONE	

EP-A-0187725	16-07-86	US-A- 4753840	28-06-88
		AU-B- 581482	23-02-89
		AU-A- 5140885	17-07-86
		CA-A- 1258031	01-08-89
		GB-A, B 2171955	10-09-86
		JP-A- 61205126	11-09-86
		US-A- 4797171	10-01-89

US-A-4673615	16-06-87	CA-A- 1239862	02-08-88
